

1.4112 X 90 CrMoV 18

Corrosion-resistant martensitic tool steel with high wear resistance, magnetic, polishable, and easy to machine for the production of knives, cutting tools, surgical instruments, ball bearings, nozzles, and knife blades.

You can obtain 1.4112 from us as a PräziPlan special dimension as well as a drawing part or guide rail.

Color coding:

Black/Green (1.4112)



1.4112 X 90 CrMoV 18
Steel glossary

269
270

WebShop:
www.stahlnetz.de



phone: +49 (0) 3 68 44 / 4 80 - 0 • fax: +49 (0) 3 68 44 / 4 80 - 55 • grp@stahlnetz.de

GEBRÜDER
RECKNABEL
Präzision in Stahl

269



1.4112 X 90 CrMoV 18

chemical composition [%]


	C	Si	Mn	P	S	Cr	Mo	V
max.	0.95	1,0	1,0	0.04	0.015	19,0	1,3	0.12
min.	0,85					17,0	0,9	0.07

Heat Treatment


Annealing: 780–840°C,
furnace cooling, maximum hardness 265 HB
Stress Relief Annealing: 600–650°C,
furnace cooling,
Hardening: 1,000–1,050°C,
quenching in oil, pressurized gas, air, or a warm bath at 500–550°C

Tempering Chart

Tempering Temperature: 1,020°C



Heat Treatment Schedule



WebShop:
270 www.stahlnetz.de



phone: +49 (0) 3 68 44 / 4 80 - 0 • fax: +49 (0) 3 68 44 / 4 80 - 55 • grp@stahlnetz.de

GEBRÜDER
RECKNABEL
Präzision in Stahl